

composition comprising] :

1 - 99% by weight of a component A, [wherein component A comprises] comprising a graft copolymer of

1 - 99% by weight of a particulate graft base A1 comprising the following monomers based on A1:

a component A11 comprising 80 - 99.99% by weight of at least one C<sub>1-8</sub>-alkyl ester of acrylic acid;

a component A12 comprising 0.01 - 20% by weight of at least one polyfunctional crosslinking monomer;

1 - 99% by weight of a graft A2 comprising the following monomers, based on A2:

a component A21 comprising 40 - 100% by weight of units of styrene, a substituted styrene, [or] a (meth)acrylate, or mixtures thereof, and

a component A22 comprising up to 60% by weight of units of acrylonitrile or methacrylonitrile;

the graft A2 comprising at least one graft shell and the graft copolymer having a mean particle size of 50 - 1000 nm;

1 - 99% by weight of a component B, [wherein component B comprises] comprising a copolymer of

a component B1 comprising 40 - 100% by weight of units of styrene, a substituted styrene, [or] a (meth)acrylate, or mixtures thereof; and

a component B2 comprising up to 60% by weight of acrylonitrile or methacrylonitrile;  
0 - 80% by weight of a component C, [wherein component C comprises] comprising a polycarbonate; and

0 - 50% by weight of a component D, [wherein component D comprises] comprising a fibrous or particulate filler or mixture thereof;

the sum of the amounts of components A, B, C and D totaling 100% by weight;

and

(3) a transparent top layer (3) of polymethyl methacrylate.

2. ( twice amended) A laminated sheet or film as claimed in claim 1, additionally comprising an interlayer (2) disposed between the top layer (3) and the substrate layer (1), the interlayer (2) having a composition different from both the composition of top layer (3) and substrate layer (1), the interlayer (2) comprising impact-modified polymethyl methacrylate, polycarbonate or [a molding composition of layer (1) as set forth in claim 1 without polycarbonate, if the molding composition layer (1) contains polycarbonate] acrylate/styrene/acrylonitrile (ASA).

Cancel claim 3.

4. (amended) [A] The laminated sheet or film [as claimed in] of claim 1 having an overall thickness of from 100  $\mu$ m to 10 mm.

5. ( twice amended) A laminated film comprising:  
a substrate layer (1') comprising a [molding composition of layer (1) as set forth in claim

1, ABS, polycarbonate, polybutylene terephthalate, polyethylene terephthalate,] polyamide, [polyetherimide, polyether ketone, polyphenylene sulfide, polyphenylene ether] or blends [thereof] of a polyamide with ABS, the substrate layer (1'), having a layer thickness of from 90 to 990  $\mu\text{m}$ ;

B3  
cont  
a transparent top layer (3') comprising polymethyl methacrylate, high-impact polymethyl methacrylate, [ABS, polycarbonate, polyethylene terephthalate, styrene-acrylonitrile copolymers,] or polyamide, [polyether sulfone or polysulfone,] the transparent top layer (3') having a layer thickness of [form] from 10 to 100  $\mu\text{m}$ ,

the substrate layer (1') [optionally] comprising special-effect colorants if the substrate layer (1') and the top layer (3') are composed of the same [molding compounds] materials, the overall thickness of the laminated film being from 100 to 100  $\mu\text{m}$ .

Cancel claim 6.

B4  
7. (twice amended) A laminated sheet or film as claimed in claim [5] 1, additionally comprising on the outer surface of the substrate layer[,]  
an adhesion layer (0) comprising an adhesion promoter and having a layer thickness of from 5 to 100  $\mu\text{m}$ .

Cancel claims 9-14.

B5  
17. (twice amended) A molding comprising a shaped laminated sheet or film as claimed in claim [3] 1, which is backsprayed or back-cast with [the molding composition of] layer [(1')] (1) as set forth in claim [5] 1 or with a polyurethane foam, or [where] which

B5  
Cond

is laminated onto a molding comprising [the molding composition of] layer [(1')] (1) as set forth in claim [5] 1, or a polyurethane foam[, is laminated with the laminated film].

Claim 19, line 3, delete "thereof".

Cancel claim 20.

Add the following new claims:

B6

21. A molding comprising a shaped laminated sheet or film as claimed in claim 2, which is backsprayed or back-cast with layer (1) as set forth in claim 2 or with a polyurethane foam, or which is laminated onto a molding comprising layer (1) as set forth in claim 2, or a polyurethane foam.

22. A molding as claimed in claim 16 in the form of an automotive exterior bodywork component.

23. A molding as claimed in claim 17 in the form of an automotive exterior bodywork component.

#### REMARKS

1. As a result of the above amendment, the following claims are under consideration in this case: 1-2, 4-5, 7-8, 15-19, and 21-23. Claims 9-14 have been withdrawn from further consideration to a nonelected invention.

2. The examiner has objected to the instant claims, and has requested that applicants reword the instant claims to make them more readable and to remove ambiguities. By the